



# nax 2400 Urethane Primer Grey



<b>Type</b>	Premium 2K Primer Surfacer
<b>Uses</b>	High quality 2K urethane primer surface specially designed for all spray applications – from spot repair to completely respray.
<b>Key Features</b>	<ol style="list-style-type: none"> <li>1) High solid and provide excellent gloss holdout</li> <li>2) Excellent filling properties</li> <li>3) Fast dry, easy wet and dry sandability</li> <li>4) Excellent adhesion</li> </ol>
<b>Colour</b>	Grey
<b>Sanding/Drying Time</b>	Dry to sand at Temp: 30°C - 60-90 mins 60°C - 30-60 mins
<b>Standard Packing</b>	Nax 2400 Urethane Primer Grey: 1 Litre Nax 240 Urethane Primer Hardener: 0.25 Litre
<b>Surface Preparation</b>	Ensure the surface of the previous coat is clean and dry, free from dirt, rust, grease oil and other foreign matters. Degreasing and cleaning with Nax Silicone Off before recoating and wipe dry with clean & dry cloth. For old paint film, wet sanding using P400-600 (hand) or dry sanding P240-320 (machine)

<b>Paint Preparation</b>	<b>Mixing Ratio</b>
Nax 2400 Urethane Primer Grey	4 Part
Nax 240 Urethane Primer hardener	1 part
Nax Premila 500 Standard Thinner	1-2 Part
<b><u>For Plastic Part</u></b>	
Nax 2400 Urethane Primer Grey	4 Part
Nax Softener	0.5 Part
Nax 240 Urethane Primer Hardener	1 Part
Nax Premila 500 Standard Thinner	1-2 Part

